RAYSTON FIBER NET

Reinforcing net



DESCRIPTION AND APPLICATIONS

Fiber glass net, alkaline resistant, white. Suitable as a reinforcing net in ceramic tile flooring repairs . Available in densities of 180 g/m2.

TECHNICAL DATA

PRODUCT INFORMATION BEFORE APPLICATION	
Composición	Fiber Glass
Weight g/m ²	180
Openings	4 mm x 4,5 mm
dimensions	
Loss on	3 a 5
ignition	
Tensile	>250 daN/ 5 cm
strength N/cm	
Coating	Synthetic resin
material	
Colour	White
Packaging	Rolls:
	1m x 50m
Storage	Keep in their original packaging, between -10°C and 50°C.
	Use before 24 months after manufacturing date

USE GUIDELINES

Spread a layer of liquid material and, while still sticky place the sheet of Rayston Fiber Net onto. Apply a second layer of liquid material covering the Rayston Fiber Net sheet. Ensure Rayston Fiber Net is dry before use. Polypropylene support nails are also available.

ENVIRONMENTAL PRECAUTIONS

Inert waste, to be treated according to local law.

OTHER INFORMATION

The information contained in this Technical Data Sheet, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project. Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Data Sheet supersedes all previous versions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies 43890-l'Hospitalet de l'Infant. Spain Tel: +34 977 822 245 - Fax: +34 977 823 977 www.kryptonchemical.com – rayston@kryptonchemical.com

Latest update:

08/02/16

Page: