



Hand-applied flexible polyaspartic topcoat for waterproofing membranes

DESCRIPTION

Impertop Fast 2k is a flexible 2-component, slow reactivity polyaspartic, that, unlike usual polyurea systems, it can be mixed and manually applied due to its moderated reaction speed while retaining a fast curing profile once applied. It is delivered in colourless or pigmented versions. Good chemical resistance. Designed as protective aliphatic topcoat for waterproofing membranes

ADVANTAGES

- Suitable for aliphatic protective topcoat for aromatic PU, polyurea waterproofing membranes.
- Fast curing
- Good adhesion properties
- High hardness and resistance, achieved with a single application.
- Excellent gloss and colour retention
- Aliphatic polyisocyanate basis. No discolouration
- Good weathering resistance

Suitable as an aliphatic topcoat for waterproofing membranes
Several test prove that these coatings inhibit corrosion in metal surfaces.

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

	Component A	Component B																
Chemical description	Polyamines solution	Solventless aliphatic polyisocyanate																
Physical state	Liquid	Liquid																
Packaging	Metal container Colourless 2.95 kg 11.00 kg Pigmented 3.85 kg 11.6 kg	Metal container Colourless: 1.05 kg 4.0 kg Pigmented 1.15 kg 3.4 kg																
Non-volatile content (%)	Colourless: 73 Pigmented: 68	100																
Flash point	35°C	>100°C																
Colour	See product list for available colours	Colourless																
Density	<table border="1"> <thead> <tr> <th>Temp (°C)</th> <th>Density (g/cm3)</th> </tr> </thead> <tbody> <tr> <td>25</td> <td>1.0 (clear) 1.05 (pigm.)</td> </tr> </tbody> </table>	Temp (°C)	Density (g/cm3)	25	1.0 (clear) 1.05 (pigm.)	<table border="1"> <thead> <tr> <th>Temp (°C)</th> <th>Density (g/cm3)</th> </tr> </thead> <tbody> <tr> <td>25</td> <td>1.15</td> </tr> </tbody> </table>	Temp (°C)	Density (g/cm3)	25	1.15								
Temp (°C)	Density (g/cm3)																	
25	1.0 (clear) 1.05 (pigm.)																	
Temp (°C)	Density (g/cm3)																	
25	1.15																	
Viscosity	<table border="1"> <thead> <tr> <th>Temp (°C)</th> <th>Viscosity (mPa.s)</th> </tr> </thead> <tbody> <tr> <td>10</td> <td>45</td> </tr> <tr> <td>25</td> <td>25</td> </tr> <tr> <td>35</td> <td>15</td> </tr> </tbody> </table>	Temp (°C)	Viscosity (mPa.s)	10	45	25	25	35	15	<table border="1"> <thead> <tr> <th>Temp (°C)</th> <th>Viscosity (mPa.s)</th> </tr> </thead> <tbody> <tr> <td>10</td> <td>725</td> </tr> <tr> <td>25</td> <td>450</td> </tr> <tr> <td>35</td> <td>260</td> </tr> </tbody> </table>	Temp (°C)	Viscosity (mPa.s)	10	725	25	450	35	260
Temp (°C)	Viscosity (mPa.s)																	
10	45																	
25	25																	
35	15																	
Temp (°C)	Viscosity (mPa.s)																	
10	725																	
25	450																	
35	260																	
A/B mixing ratio	Colourless A=100, B=36 by weight A=100, B=31.5 by volume Pigmented A=100, B=29 by weight A=100, B=27.5 by volume																	
Mixture properties (25°C)	Density: 1.04 g/cm3 Viscosity: 105 mPa.s (clear), 115 mPa.s (pigmented)																	
Colour	Non-volatile content: 80% (clear), 75% (pigmented) Colourless if not pigmented. Available colours in the product list																	
Pot life	<table border="1"> <thead> <tr> <th>Conditions</th> <th>Pot life (min)</th> </tr> </thead> <tbody> <tr> <td>22°C 40%rh</td> <td>30</td> </tr> </tbody> </table>	Conditions	Pot life (min)	22°C 40%rh	30													
Conditions	Pot life (min)																	
22°C 40%rh	30																	

Storage	Keep at 10°C and 30°C.
Use before	12 months after manufacture date.

INFORMATION ON THE FINAL PRODUCT

Final state	Solid polyaspartic/polyurethane coating
Colour	Colourless. Other colours available under request
Density	1.07 g/cm3 (Colourless) 1,15 g/cm3 (Pigmented)
Hardness (shore)	55D
Mechanical properties	Elongation at break: 150% Tensile strength: 22 MPa
UV resistance	Colour stable under sunlight

SUPPORT REQUIREMENTS

Support must have enough mechanical strength, free from any vapour or water pressure. Support must also be clean, dry and free from poorly-adhesive areas. Recommended support temperature: 10°C to 25°C.

ENVIRONMENTAL CONDITIONS

Recommended air temperature: 10°C to 30°C
Recommended humidity: less than 60%

SUPPORT PREPARATION

On recently applied sprayed waterproofing membrane:

For better adhesion apply topcoat shortly (30 min) after application of the membrane.

Older membranes: gentle sanding and cleaning with rayston solvent and use of PU primer is advised.

MIXING

Open component A container. Stir using a low-speed stirrer preventing an excessive air bubbling, until dispersion of fillers. Pour component B in it and stir gently for 2 minutes. Transfer the mixture to a bigger container and check there is no unmixed product left.

APPLICATION

Apply by roller. Airless equipment is not recommended due to safety reasons. Reaction rate increases with the size of the mixtures; therefore it is advised not to mix more amount of product than that can be easily applied in a 15 minutes period. Otherwise, application could be difficult or the final appearance could be affected

RECOMMENDED QUANTITIES

Impertop Fast 2k can be applied in a wide thickness range. It is recommended to apply 200 to 500 microns when dry. (200 to 600 g/m2 wet film).

CURING TIME

Curing time depends strongly on the local conditions. Curing speed will increase with temperature and humidity. The following table gives approximate values for 200 g/m2 applications. Thicker coats will give longer curing times.

Conditions	Touch to Dry (h)	Total (h)
22°C, 40% rh	1.5	3
8°C, 50% rh	2.5	5

RECOATING

Only one coat is usually needed

RETURN TO SERVICE

Under most conditions a light traffic is permitted about 2 hours after it is dry to touch. A normal use is recommended only the following day.





Hand-applied flexible polyaspartic topcoat for waterproofing membranes

TOOL CLEANING

Component A and B can be cleaned with solvent Rayston. Cured product cannot be dissolved, unless special stripping products are used. Due to its fast curing rate, A+B mixture staining must be cleaned as soon as possible.

CLEANING AND MAINTENANCE

A daily water scrubbing is allowed. Solvents may seriously damage the surface.

FAQ

Problem	Answer
It can be thinned?	Not usually needed. If desired, some solvent can be added, but keep in mind that this will result in a longer drying time, and colour could be affected. Solvents must be always polyurethane grade. They must be absolutely free from alcohols or water, or any substance that can affect the crosslinking reaction. Recommended solvents are xylene or methoxypropyl acetate (PMA).
Is spreading of quartz sand allowed?	Yes. The pot life gives enough time for the application of antislip additives (Quartz sand, bauxite, etc) between two coats. Please refer to Krypton Chemical advice for further information on the application details.
Can it be pigmented?	Please refer to Krypton Chemical advice for colour options and procedures

MAINTENANCE

A daily water scrubbing is allowed. Solvents may seriously damage the surface

SAFETY

Impertop Fast 2k contains isocyanates and flammable solvents. Always follow the instructions provided in the material safety data sheet and take the precautions described there. As a general rule, suitable ventilation must be ensured and any skin contact avoided. This product is intended to be used only for the uses and in the way here described. Sprayed application methods are not recommended due to health/safety reasons. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses..

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled taking the same precautions as if they were full. Containers must be considered as hazardous waste, to be transferred to an authorized waste manager.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.