

POLYUREA PRIMER



Fast curing polyurea primer

DESCRIPTION

Fast curing, cold-applied two component pure polyurea based primer. Especially designed for applications on rigid, porous and dry supports.

APLICACIÓN

as adhesion layer, sealant and strengthener for rigid, porous and dry substrates. sellante (concrete, cement) before the application of polyurethane or polyurea waterproofing membranes.

DATOS TÉCNICOS

INFORMACIÓN SOBRE EL PRODUCTO ANTES DE LA APLICACIÓN

	Componente A	Componente B																
Chemical description	Polyisocyanate solution	Poliamina																
Physical state	Líquido	Líquido																
Packaging (predosed kit A+B)	Metal container 20 kg 4 kg	Metal container 2 kg 0.4 kg																
Non-volatile content (%)	60% en peso	100																
Flash Point	36°C	81°C																
Colour	light yellow	light yellow																
Density	<table border="1"><thead><tr><th>Temperature (°C)</th><th>Density (g/cm3)</th></tr></thead><tbody><tr><td>25</td><td>0.95</td></tr></tbody></table>	Temperature (°C)	Density (g/cm3)	25	0.95	<table border="1"><thead><tr><th>Temperature (°C)</th><th>Density (g/cm3)</th></tr></thead><tbody><tr><td>25</td><td>0.9</td></tr></tbody></table>	Temperature (°C)	Density (g/cm3)	25	0.9								
Temperature (°C)	Density (g/cm3)																	
25	0.95																	
Temperature (°C)	Density (g/cm3)																	
25	0.9																	
Viscosity (Brookfield)	<table border="1"><thead><tr><th>Temperature (°C)</th><th>Viscosity (mPa.s)</th></tr></thead><tbody><tr><td>10</td><td>300</td></tr><tr><td>25</td><td>170</td></tr><tr><td>35</td><td>110</td></tr></tbody></table>	Temperature (°C)	Viscosity (mPa.s)	10	300	25	170	35	110	<table border="1"><thead><tr><th>Temperature (°C)</th><th>Viscosity (mPa.s)</th></tr></thead><tbody><tr><td>10</td><td></td></tr><tr><td>25</td><td><20</td></tr><tr><td>35</td><td></td></tr></tbody></table>	Temperature (°C)	Viscosity (mPa.s)	10		25	<20	35	
Temperature (°C)	Viscosity (mPa.s)																	
10	300																	
25	170																	
35	110																	
Temperature (°C)	Viscosity (mPa.s)																	
10																		
25	<20																	
35																		
VOC	393 g/L, 40%	nd																
A/B Ratio	A=100, B=10 in weight A=100, B=10.5 in volume																	
Mixture properties	Density: 0.90-0.95 g/cm3 Viscosity: 95 mPa.s Colour: slightly yellow																	
Pot life	<table border="1"><thead><tr><th>Conditions (100g)</th><th>Pot life (min)</th></tr></thead><tbody><tr><td>25°C, 40% hr</td><td>60</td></tr></tbody></table>	Conditions (100g)	Pot life (min)	25°C, 40% hr	60													
Conditions (100g)	Pot life (min)																	
25°C, 40% hr	60																	
	In contact with air, the product can form a surface skin in the packaging Remove the skin, if formed, and continue the application. High temperatures and humidities reduce working time																	
Storage	Store between 10° and 30°C, protected from humidity.																	
Expiration	12 months after manufacturing date, in its original, unopened container.																	

INFORMATION ON THE FINAL PRODUCT

Final State	Solid membrane
Colour	Colourless, slightly yellow
Hardness (Shore)	70D
Density	1,35 g/cm3
Mechanical properties	Max. elongation: 53% Tensile stress: 37 MPa

Adhesion

Concrete: >5 N/mm2 (EN 13892-8)

UV resistance

Polyurea Primer is an aromatic product. It will turn to yellow when exposed to sunlight, without impairment of its mechanical properties.

Thermal

resistance

Stable up to 80°C.

SUPPORT REQUIREMENTS

Support should present the following mechanical properties:

Cohesion: minimum 1,5 MPa.

Compressive strength: minimum 25 MPa.

Support must be completely free of water or water vapour.

The surface must be clean, dry and free of any area with less or no grip, and with a moisture content of less than 4%. It should be especially free of oil stains, grease, cured product, and any substance that could interfere with adhesion. Substrate temperature should be between 10 ° C and 25 ° C.

If you suspect the presence of moisture in the support, use an appropriate primer. Consult Krypton Chemical for the types of primer.

On concrete or fresh mortar, you must wait at least 21 days before applying this system so that drying of the support is allowed

CONSUMPTION

Expect a consumption of 300-400 g/m2

AMBIENTAL CONDITIONS

Air temperature should be between +10 and +30 °C. Relative humidity shouldn't exceed 60%.

MIXING

Open the container of component A. Shake the product mechanically at low speed to avoid excessive intake of air. Homogenization of component A should be in about 2 minutes. Then pour component B into the container of component A and mix in the same way for 2 minutes. Pour the mixture into a larger container and verify that there remains no material unmixed.

CURING TIME

Curing time depends strongly on the ambient conditions. The higher the temperature and humidity are, the faster Polyurea Primer cures

Conditions	Dry to touch (minutes)
25°C, 40% hr, 200 g/m2	25
10°C, 50% hr, 200 g/m2	45

TOOL CLEANING

Components A and B can be cleaned with Rayston solvent. Cured product can only be removed with special Paint Stripper.


SECURITY

This product contains isocyanates and polyamines. Always follow the instructions provided in the material safety data sheet and take the precautions described there. As a general rule, suitable ventilation must be ensured and any skin contact avoided. This product is intended to be used only for the uses and in the way here described. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

POLYUREA PRIMER



Fast curing polyurea primer

We recommend studying deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The

application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.