

HUMIDITY PRIMER



Water-based epoxy primer

DESCRIPTION AND APPLICATION

Moist surfaces are troublesome when treated with any synthetic resin, both because of immediate adhesion difficulties and problems arising afterwards because of the upward water pressure.



In many cases, material and time constraints force applicators to work on less-than-optimal support conditions, and a moisture-addressed product is needed in order to:

- Minimize adhesion failures.
- Avoid blistering due to the water pressure from below (support saturation)
- Avoid air bubbles, due to the water vapour pressure which cannot be released (mostly encountered in elastic membrane treatments.
- Incompatibility of the support with one-component, moisture-cured polyurethane resins.

Humidity Primer is the best solution as a primer for waterproofing or flooring polyurethane application on supports with moisture content greater than 4%. Nevertheless, this product is not useful when moisture has a freatic origin, with pressures greater than 1,5 N/mm².



Humidity Primer is a 2-component, water based epoxy resin. Components, once mixed, are totally compatible with moist supports, and the resulting polymerized product is a crystalline material with high adhesion and tensile strength. It effectively blocks residual moisture flow and prevent blistering of the polyurethane coating applied on top.

This product is useful for any kind of waterproofing project, involving polyurethane sealing, such as:

- Roof and wall refurbishments.
- Waterproofing treatment of tanks and other water management facilities.
- Floorings in moisture-affected environments.

CERTIFICATIONS

ETA: European Technical agreement document N° 06/0263 -CE marking: 10 and 25 years.



TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

| | Component A | Component B |
|---------------------------------|-------------------------------------|----------------------------------------|
| Chemical description | Epoxy resin | Aqueous polyamine solution |
| Physical state | Liquid | Liquid |
| Packaging | Metal container 5,2 kg 1,4 kg | Plastic container 12,8 kg 3,6 kg |
| Non-volatile content (%) | Approx. 100% | 31% |
| Flash point | >100°C | >100°C |
| Colour | Colourless | Slightly yellow |

Density

| Temp (°C) | Density (g/cm ³) | Temp (°C) | Density (g/cm ³) |
|-----------|------------------------------|-----------|------------------------------|
| 25 | 1,14 | 25 | 1,05 |

Viscosity

| Approximate values Brookfield | Temp (°C) | Viscosity (mPa.s) | Temp (°C) | Viscosity (mPa.s) |
|-------------------------------|-----------|-------------------|-----------|-------------------|
| | 35 | 70 | 35 | 170 |
| | 25 | 150 | 25 | 280 |
| | 15 | 300 | 15 | 500 |
| | 5 | 500 | 5 | 1800 |

VOC

0 2 g/L, 2%

A/B mixing ratio

A=100, B=244 by weight
A=100, B=266 by volume

Mixture properties

Density: 1,07g/cm³ at 23°C
Viscosity: 1300 mPa.s at 23°C
Colour: milky white

Pot life

| Temp (°C) | Pot life (100, min) |
|-----------|---------------------|
| 10 | 90 |
| 25 | 45 |
| 35 | 30 |

Storage

Keep between 10° and 30°C. Frost-sensitive.
Component A may crystallize if stored for protracted periods under certain conditions. If this occurs, it can be restored to its original condition by heating it to 70 - 80 °C and stirring it thoroughly.

Use before

12 months after manufacturing date.

INFORMATION ON THE FINAL PRODUCT

| | |
|------------------------------|------------------------------------------------------------------------------------------------------|
| Final state | Solid, hard, film |
| Colour | Light yellow |
| Hardness (shore) | 64D |
| Mechanical properties | Maximum elongation: 3,2% Tensile strength: 39 MPa (EN-ISO 527-3) |
| Tear resistance | 7,2 N/mm |
| Solid film density | 1,3 g/cm ³ |
| UV resistance | This product shows a very slight yellowing upon UV exposure, without loss of mechanical properties.. |
| Chemical resistance | Permanent contact (3 days, 80°C) |

| Chemical | %weight gain |
|---------------------------|--------------|
| Water | 5 |
| Methoxypropyl acetate | 25 |
| Isopropyl alcohol | 15 |
| Skydrol | 0 |
| Xylene | 10 |
| Ammonia (3%) | 10 |
| Acetone | 35 |
| Diesel | 5 |
| Hydrogen peroxide | 10 |
| Sodium hydroxide (40 g/L) | 10 |
| Bleach | 5 |
| Sulphuric acid (10%) | 30 |
| Sulphuric acid (30%) | 30 |
| Sulphuric acid (50%) | 30 |
| Acetic acid (10%) | 15 |

Surface contact (24h, room temperature, 5=ok, 0=not recommended)

| Chemical | Result |
|-----------------------|--------|
| Water | 5 |
| Ethyl alcohol | 5 |
| Engine oil | 5 |
| Vinegar | 5 |
| Hydrogen peroxide | 5 |
| Sulphuric acid (10%) | 4 |
| Sulphuric acid (30%) | 4 |
| Sulphuric acid (50%) | 4 |
| Isopropyl alcohol | 5 |
| Xylene | 4 |
| Ammonia (3%) | 5 |
| Diesel | 5 |
| Methoxypropyl acetate | 5 |
| Acetic acid (10%) | 3 |
| Bleach | 5 |
| Sodium hydroxide | 5 |



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890-l'Hospitalet de l'Infant- Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com


Latest update:

08/02/2016

Page:

1/2

HUMIDITY PRIMER



Water-based epoxy primer

| | |
|----------|---|
| (40 g/L) | |
| Acetone | 2 |
| Skydrol | 5 |

Adhesion strength

| Surface | Adhesion strength (mPa) |
|----------|-------------------------|
| Concrete | >4,9 |

| | |
|------------------------|-------------------|
| Use temperature | Stable up to 80°C |
| Gloss (60°) | 14% |

SUPPORT REQUIREMENTS

In order to achieve a good penetration and bonding, support must be:

1. Flat and levelled (Product is self-levelling)
2. Compact and cohesive (pull off test must show a minimum resistance of 1,4 N/mm²).
3. Even and regular surface
4. Free from cracks and fissures. If any, they must be previously repaired.
5. Clean and dry, free of dust, loose particles, oils, organic residues or laitance

RECOMMENDED ENVIRONMENTAL CONDITIONS

Support temperature should be between 15°C and 40°. At higher temperatures, specific precautionary measures must be taken. Please follow manufacturer advice. Application under low temperature and high humidity conditions is not recommended

SUPPORT PREPARATION

Concrete surfaces must be previously prepared by sandblasting or any other suitable means. Remove all dust and loose material before priming.

MIXING

Stir and homogenise thoroughly component A and B using a low-speed stirrer. The mixture turns to a whitish, milky dispersion. After application, the milky layer should turn to a colourless film in a one to two hours period, depending on temperature, humidity and thickness.

APPLICATION

Apply 200 to 500 g/m², by brush or roller. Higher quantities may lead to white/translucent areas and poor appearance.

On very absorbent substrates, dilution is allowed. Use 10 to 20% water. On hot surfaces (e.g. recently exposed to sun), moist the surface before starting application.

Application in excess can lead to resin retraction upon water evaporation. Do not exceed the recommended application quantities. If some white spots appear after curing, they must be removed before application of following coats.

CURING TIME

Data for a 500 g/m² application.

High temperature and low humidity favours the drying process. High humidity conditions make the initial milky film to remain white and sticky.

| Conditions | Dry to touch (h) |
|--------------|--------------------|
| 25°C, 5%hr | 6 |
| 25°C, 90% hr | 10 (milky) |
| 35°C, 20% hr | 2 |
| 6°C, 50°C | >100 |
| -15°C | >100, always milky |

REAPPLICATION

A second coat may be applied, if needed, from the moment when the first coat is dry to touch, and not later than 24 hours.

RETURN TO SERVICE

When used as a primer for polyurethane waterproofing or flooring jobs where appearance is important, it is recommended to ensure Humidity Primer is fully cured and dry, by measuring the moisture content on the Primer film if necessary. If some of the initial water remains when a moisture-curing polyurethane is applied, some blisters may develop.

TOOL CLEANING

Component A can be cleaned using Rayston Solvent. Component B and the unreacted AB mixture can be cleaned with water.

QUESTION AND ANSWER

| Problem | Question | Causes | Solutions |
|-------------------------------|----------------------|--------------------|---------------------------------|
| Film remains white and sticky | Cold, humid weather? | Slow reaction rate | Remove and change primer system |

SAFETY

Epoxy components are potentially sensitizing. Always follow instruction provided in the Material Safety Data Sheet. As a general rule, suitable skin and eye protection must be worn. This product is intended to be used only for the uses and in the way here described. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the containers still have some material left, do not mix with other product before considering the risk of potential dangerous reactions. Never mix in volumes larger than 5 litres in order to prevent a dangerous heat evolution

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.

